

DuPont™ Vespel® SCP-50094

POLYIMIDE ISOSTATIC SHAPES

TYPICAL ISO PROPERTIES

DuPont™ Vespel® SCP-50094 is a proprietary polymer. It is designed for demanding applications that require high temperature and wear resistance.

The typical values presented below are preliminary results and are subject to revision.

Mechanical Property	Temperature	Pressure	ASTM Method	SI (English) Units	Typical Values
Tensile Strength	23°C (73°F) 260°C (500°F)	—	D-638 D-1708 Specimen	MPa (kpsi)	124 (18.0) 55 (8.0)
Tensile Elongation	23°C (73°F) 260°C (500°F)	—	D-638 D-1708 Specimen	%	4.3 13
Young's Modulus	23°C (73°F) 260°C (500°F)	—	D-638 D-1708 Specimen	MPa (kpsi)	4,140 (600) 2,350 (340)
Flexural Strength	23°C (73°F) 260°C (500°F)	—	D-790	MPa (kpsi)	200 (29) 96 (14)
Flexural Modulus	23°C (73°F) 260°C (500°F)	—	D-790	MPa (kpsi)	6,370 (923) 3,540 (514)
Compressive Strength	23°C (73°F) 260°C (500°F)	—	D-695	MPa (kpsi)	385 (56) 450 (65)
Compressive Strain, Ultimate	23°C (73°F) 260°C (500°F)	—	D-695	MPa (kpsi)	41 63
Compressive Stress at 10% Strain	23°C (73°F) 260°C (500°F)	—	D-695	MPa (kpsi)	220 (31.9) 81 (11.7)
Deformation Under Load after 24 hours	23°C (73°F)	14 MPa (2 kpsi)	D-621	% deformation	0.05
Compressive Creep 10 hours 100 hours 1000 hours	23°C (73°F)	10 MPa (1.5 kpsi)	D-2990	%	0.02 0.02 0.05
Compressive Creep 10 hours 100 hours 1000 hours	23°C (73°F)	14 MPa (2.5 kpsi)	D-2990	%	0.03 0.05 0.07
Rockwell "E" Hardness	—	—	D-785	—	91
Poisson's Ratio	23°C (73°F) 260°C (500°F)	—	D-638	—	0.34 0.34



The miracles of science™

DuPont™ Vespel® SCP-50094 Typical ISO Properties *continued*

Thermal Property	Temperature	Pressure	ASTM Method	SI (English) Units	Typical Values
Coefficient of Thermal Expansion • Perpendicular • Parallel	50 – 150°C (122 – 302°F)	—	E-831	m/m·°C or m/m·K (in/in·°F)	42.7 × 10 ⁻⁶ (23.7 × 10 ⁻⁶)
Thermal Conductivity	50°C (122°F) 100°C (212°F) 300°C (572°F)	—	F-433	W/m·K (Btu/hr·in·°F)	0.59 (0.03) 0.66 (0.03) 0.58 (0.03)
Specific Heat	60°C (140°F)	—	E-1269	J/kg·°C (Btu/lb·°F)	9.2 × 10 ⁵ (0.22)
Wear Property	Velocity	Pressure	Method	SI (English) Units	Typical Values
Coefficient of Friction, Unlubricated, Air • 0.88 (25K) PV • 3.50 (100K) PV • 10.50 (300K) PV	0.7 m/s (134 fpm) 2.0 m/s (400 fpm) 3.0 m/s (585 fpm)	1.3 MPa (187 psi) 1.7 MPa (250 psi) 3.5 MPa (500 psi)	Falex	—	0.25 0.07 0.11
Wear Factor, Unlubricated, Air • 0.88 (25K) PV • 3.50 (100K) PV • 10.50 (300K) PV	0.7 m/s (134 fpm) 2.0 m/s (400 fpm) 3.0 m/s (585 fpm)	1.3 MPa (187 psi) 1.7 MPa (250 psi) 3.5 MPa (500 psi)	Falex	mm-sec/MPa-m-hr (in ³ -min/ft-lb-hr)	1.7 × 10 ⁻³ (24 × 10 ⁻¹⁰) 0.8 × 10 ⁻³ (11 × 10 ⁻¹⁰) 1.2 × 10 ⁻³ (17 × 10 ⁻¹⁰)
Other Property	Temperature	Time	ASTM Method	SI (English) Units	Typical Values
Specific Gravity	23°C (73°F)	—	D-792	—	1.50
Water Absorption	23°C (73°F)	24 hours	D-570	% weight change	0.06

Phone: 800-222-VESP (8377)
Fax: 302-999-2311
E-mail: web-inquiries.DDF@usa.dupont.com

Web: vespel.dupont.com

The data listed here fall within the normal range of properties, but they should not be used to establish specification limits nor used alone as the basis of design. The DuPont Company assumes no obligations or liability for any advice furnished or for any results obtained with respect to this information. All such advice is given and accepted at the buyer's risk. The disclosure of information herein is not a license to operate under, or a recommendation to infringe, any patent of DuPont or others. Since DuPont cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information.

CAUTION: This product is not permitted to be sold for use in medical applications involving any implantation in the human body or where contact with internal body fluids or tissues will equal or exceed 24 hours. For applications involving contact of less than 24 hours, see "DuPont Medical Caution Statement" H-50102 or contact your DuPont sales representative.

Copyright © 2009 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, and Vespel® are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

K-21997 (04/07/09) Printed in the U.S.A.



The miracles of science™